



Sipchem PBT-R1-G6-010

Polybutylene Terephthalate Resin

Product description: Sipchem PBT-R1-G6-010 is a Polybutylene Terephthalate resin, manufactured by Sipchem Chemical Company in The Kingdom of Saudi Arabia using an Inventa-Fischer Technology.

PBT-R1-G6-010 is a high viscosity neat PBT resin

Applications: Compounding

| Properties | Typical Value | Unit | Test Method |
|---|---------------|-------------------|-------------|
| PHYSICAL | | | |
| Density | 1.31 | g/cm ³ | ASTM D1505 |
| Melt Flow Rate (250°C/2.16kg) | 10 | g/10 min | ASTM D1238 |
| Intrinsic Viscosity | 1.3 | dL/gr | ASTM D2857 |
| Carboxyl End Group | < 30 | meq/kg | ISO 2114 |
| Colour (b*) | < 3 | - | ASTM D6290 |
| MECHANICAL | | | |
| Tensile Strength | 56.4 | MPa | ASTM D638 |
| Elongation at Yield | 3.5 | % | ASTM D638 |
| Flexural Modulus | 2160 | MPa | ASTM D790 |
| Flexural Strength | 78.9 | MPa | ASTM D790 |
| Flexural Strain at Flexural Strength | 8.1 | % | ASTM D790 |
| Izod Impact Strength - Unnotched at +23°C | NB | J/m | ASTM D256 |
| Izod Impact Strength - Notched at +23°C | 29.8 | J/m | ASTM D256 |
| THERMAL | | | |
| Melting Temperature | 225 | °C | ASTM D3418 |
| Heat Deflection Temperature, 1.80 MPa | 49.4 | °C | ASTM D648 |
| Vicat Softening Temperature | 171.3 | °C | ASTM D1525 |
| Burning Behaviour | HB | Class | IEC 60695 |

These are typical properties: these are not to be construed as specifications.

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your Sipchem Representative for compliance with Food Contact Regulation.

Contact Details:

Company Name: SIPCHEM
Address: P.O Box 130, Al-Khobar 31952
Website: www.sipchem.com
Phone: +966 13801 9392
Email: marketing@sipchem.com
Fax: +966 13801 0095

Issue Date: February 2017 (v.3.2)

The preliminary information in this document is provided for pre-marketing purposes only, and relates only to the named product or materials when not in combination with any other product or materials. The information and recommendations presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made. Before using one of the products mentioned herein, customers and other users should take care in determining the suitability of such product for the intended use. Sipchem therefore, does not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.