

Sipchem LD 0322 GO

Low Density Polyethylene Resin

Product description: Sipchem LD 0322 GO is a Low Density Polyethylene resin, manufactured by IPC an affiliate of Sipchem in The Kingdom of Saudi Arabia using an Exxon-Mobil high-pressure tubular process. LD 0322 GO is designed to offer high strength combined with medium optical properties.

Applications: Agricultural Film, Blend Partner, Construction Film, Foam, Heavy Duty Bags, High Performance Collation Shrink, Pallet Shrink Film, Profile Extrusion.

Additives: Thermal Stabiliser: 500 ppm Antiblock: No Slip: No

Properties	Typical Value	Unit	Test Method
Melt Index (190°C / 2.16 kg)	0.33	g/10 min	ASTM D1238
Density	0.922	g/cm ³	ASTM D1505
Melting Point	109	°C	ASTM D3418
Tensile Strength at Yield MD	12	MPa	ASTM D882
Tensile Strength at Yield TD	11	MPa	ASTM D882
Tensile Strength at Break MD	24	MPa	ASTM D882
Tensile Strength at Break TD	22	MPa	ASTM D882
Elongation at Break MD	500	%	ASTM D882
Elongation at Break TD	650	%	ASTM D882
Secant Modulus MD – 1% Secant	210	MPa	ASTM D882
Secant Modulus TD – 1% Secant	240	MPa	ASTM D882
Drop Dart Impact	320	g	ASTM D1709A
Elmendorf Tear Strength MD	400	g	ASTM D1922
Elmendorf Tear Strength TD	750	g	ASTM D1922
Gloss (45°C)	54	g	ASTM D2457
Haze	11	%	ASTM D1003

1. These are typical properties: these are not to be construed as specifications.
2. This product is not intended for use in medical applications and should not be used in any such applications.
3. Contact your Sipchem Representative for potential food contact application compliance.

Compliance & Product Stewardship Department

Contact Details:

Website: www.sipchem.com
Email: marketing@sipchem.com
Phone: +966 13 359 3372

Disclaimer

Before using the product listed above, customers and other users should take care in determining the suitability of such product for the intended use. SIPCHEM do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.