

Sipchem EVA 3514

14.4% Ethylene - Vinyl Acetate [EVA] copolymer

Product description: Sipchem EVA 3514 is a 14.4% ethylene - vinyl acetate copolymer resin, manufactured by IPC[†] in The Kingdom of Saudi Arabia using an Exxon-Mobil high-pressure tubular process.

Film made from EVA 3514 exhibits very high impact strength, high clarity and excellent heat sealability.

Applications: Meat Packaging, Heat Seal Layer.

Resin properties:

| Physical properties | Typical Value ¹ | Unit | Test Method |
|-------------------------------|----------------------------|-------------------|-------------|
| Melt Index (190°C / 2.16 kg) | 3.5 | g/10 min | ASTM D1238 |
| Vinyl Acetate Content | 14.4 | wt% | IPC Method |
| Density | 0.933 | g/cm ³ | IPC Method |
| Melting Point | 88 | °C | ASTM D3418 |
| Vicat Softening Temperature | 64 | °C | ASTM D1525 |
| Tensile Strength at Break MD | 31 | MPa | ASTM D882 |
| Tensile Strength at Break TD | 27 | MPa | ASTM D882 |
| Elongation at Break MD | 300 | % | ASTM D882 |
| Elongation at Break TD | 730 | % | ASTM D882 |
| Secant Modulus MD – 1% Secant | 66 | MPa | ASTM D882 |
| Secant Modulus TD – 1% Secant | 74 | MPa | ASTM D882 |
| Drop Dart Impact | 320 | g | ASTM D1709A |
| Elmendorf Tear Strength MD | 80 | g | ASTM D1922 |
| Elmendorf Tear Strength TD | 60 | g | ASTM D1922 |

1. These are typical properties: these are not to be construed as specifications.
2. This product is not intended for use in medical applications and should not be used in any such applications.
3. Contact your Sipchem Representative for potential food contact application compliance.

[†]IPC [International Polymers Company]
PO Box 12021
Jubail Industrial City - 31961
Kingdom Of Saudi Arabia

IPC is an affiliate of Sipchem

October 2013 – v 3.6
Page 1/1

+966 3 801 9255

The preliminary information in this document is provided for pre-marketing purposes only, and relates only to the named product or materials when not in combination with any other product or materials. The information and recommendations presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made. Before using one of the products mentioned herein, customers and other users should take care in determining the suitability of such product for the intended use. Sipchem and International Polymers Company therefore, do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.